





ABETONE CLUB



Specification/tolerances in according EN 1307

Costruzione	Technique de fabrication	Construction	Herstellungsverfahren
Moquette Wilton superficie velluto-riccio	Moquette Wilton à velours coupé/bouclé	Wilton carpet cut/loop pile	Wilton teppich schnitt-schlingenpol
Composizione 100% Lana	Composition du velours 100% Laine	Pile composition 100% Wool	Polnutschicht 100% Wolle
Sottofondo Juta/sintetico	Dossier Jute/synthétique	Secondary backing Jute/synthetic	Rückenausrüstung Jute/synthetik
Punti al m² ± 96000	Touffes au m² ± 96000	Stitches per m² ± 96000	Knoten m² ± 96000
Altezza pelo ± 6 mm	Hauteur du velours ± 6 mm	Pile height ± 6 mm	Polhöhe ± 6 mm
Altezza totale ± 8 mm	Hauteur totale ± 8 mm	Total height ± 8 mm	Gesamtdicke ± 8 mm
Peso della fibra ± 1211 g/m ²	Poids du velours ± 1211 g/m ²	Yarn weight ± 1211 g/m ²	Polgewicht ± 1211 g/m ²
Peso totale ± 2207 g/m ²	Poids total ± 2207 g/m ²	Total weight ± 2207 g/m ²	Gesamtgewicht ± 2207 g/m ²
Larghezza rotolo 400 cm	Largeur du rouleau 400 cm	Roll width 400 cm	Breite 400 cm
Famiglia Wilton 100% lana	Famiglia Wilton 100% lana	Famiglia Wilton 100% lana	Famiglia Wilton 100% lana

Note-Marine Equipment
Fire certification: range certified



Colour fastness to light	≥ 5 (4 pastel shade)	Thermal resistance m ² K/W	≤ 0,17
Insulation impact noise ΔLw	32 dB	Body voltage walking test kV	≤ 2
Acoustical absorption α _w	0,23		

RESISTENZA – WEARABILITY RESISTANCE - STRAPAZIERWERT				COMFORT – COMFORT CONFORT - KOMFORTWERT			
estrema extreme extrême extrem	elevata high élevée stark	normale good normale normal	sufficiente normal suffisante gering	medio medium moyen einfach	buono good bon gut	alto very good élevé hoch	ottimo excellent excellent luxuriös

Approved by Tecniq Management: M. Medica

Date: 30/05/2017